



**HYDRO**

**Precision drawn tubes available alloys in North America**

Composition in weight percent maximum unless shown as range or a minimum

<b>Alloy</b>	<b>Al</b>	<b>Si</b>	<b>Fe</b>	<b>Mg</b>	<b>Mn</b>	<b>Cu</b>	<b>Zn</b>	<b>Cr</b>	<b>Ti</b>	<b>Other</b>
3003	remain der	.6	.7	-	1.0 – 1.5	.05 - .2	.1	-	-	1.5
6063	remain der	.2 - .6	.35	.45 - .9	.1	.1	.1	.1	.1	.15
HA9048	Long Life Alloy									