



Extruded tubes available alloys in North America

Composition in weight percent maximum unless shown as range or a minimum

| Alloy | Al | Si | Fe | Mg | Mn | Cu | Zn | Cr | Ti | Other |
|--------|-----------------|-------------|---------|-----|-----------|----------|-----|----|-----|-------|
| 1050 | Min.99.5 | .6 | .7 | - | 1.0 – 1.5 | .05 - .2 | .1 | - | - | 1.5 |
| 1060 | Min.99.6 | .25 | .35 | .03 | .03 | .05 | .05 | - | .03 | .03 |
| 1235 | Min.99.35 | .65 Si + Fe | | .05 | .05 | .05 | .1 | - | .06 | .03 |
| 1435 | Min.99.35 | .15 | .3 - .5 | .05 | .05 | .02 | .1 | - | .03 | .03 |
| 3003 | remainder | .6 | .7 | - | 1.0 – 1.5 | .05 - .2 | .1 | - | - | .15 |
| 3102 | remainder | .4 | .7 | - | .5 - .4 | .1 | .3 | - | .1 | .15 |
| HA3725 | Long Life Alloy | | | | | | | | | |